

**DRAFT AMENDMENT NO. 1 MARCH 2024**  
**TO**  
**IS 17861: 2022 TEXTILE BOOTS WITH POLYMERIC SOLE**  
**(JUNGLE BOOTS) — SPECIFICATION**

*(Page 2, clause 5.7.4)* — Insert the following new clause after **5.7.4**;

**5.7.5 Water Repellency and Water Resistance**

When Type 1 Upper material tested in accordance with IS 390, the water repellency shall be minimum 90 rating.

When Type 2 Upper material tested in accordance with IS 7016(Part 7), the upper material shall be water resistance.

*(Page 2, clause 5.8)* —Substitute the existing clause with the following clause:

**5.8 Lining**

Lining shall be provided for Type 1 and Type 2 boots.

*(Page 3, clause 5.9.1)* — Insert the following new clause after **5.9.1**

**5.9.2 Abrasion Resistance Test**

When Outer toe cap is subjected to test in accordance with IS 15298(Part 1), the outer toe cap shall not show any significant damage for 7000 cycles.

*(Page 4, clause 5.16.2)* — Substitute the existing clause with the following clause:

When tested as per method given in 8.1 of IS 15298 (Part 1), the thickness ( $d_1$ ) shall not be less than 4 mm and the cleat height ( $d_2$ ) shall not be less than 2.5 mm for type 1.

When tested as per method given in 8.1 of IS 15298 (Part 1), the thickness ( $d_1$ ) shall not be less than 4 mm and the cleat height ( $d_2$ ) shall not be less than 6 mm for type 2.

When PU rubber sole is produced, for adhesion purposes of unit rubber sole with PU middle sole , inverse cavity at face part of rubber sole shall not be less than 3mm and such cavities shall be distributed in such manner that proper bonding takes place all over the surface .

*(Page 4, clause 5.16.7)* — Substitute the existing clause with the following clause:

When outsoles are tested in accordance with **8.3** of IS 15298 (Part1), the relative volume loss shall not be greater than 200 mm<sup>3</sup>.