

DRAFT AMENDMENT NO. 1 MARCH 2024
TO
IS 17861: 2022 TEXTILE BOOTS WITH POLYMERIC SOLE
(JUNGLE BOOTS) — SPECIFICATION

(Page 2, clause 5.7.4) — Insert the following new clause after **5.7.4**;

5.7.5 Water Repellency and Water Resistance

When Type 1 Upper material is tested in accordance with IS 390, the spray rating scale shall be minimum 4.

When Type 2 Upper material is tested in accordance with IS 7016(Part 7), the material shall be water resistance.

(Page 2, clause 5.8) — Substitute the existing clause with the following clause:

5.8 Lining

Lining shall be provided for Type 1 and Type 2 boots.

(Page 3, clause 5.9.1) — Insert the following new clause after **5.9.1**

5.9.2 Abrasion Resistance Test

When tested in accordance with IS 6994(Part 6), the outer toe cap shall not develop any hole through the full thickness before 2 000 cycles.

(Page 4, clause 5.16.2) — Substitute the existing clause with the following clause:

When tested in accordance with IS **15298 (Part 1)**, the thickness (d_1) shall not be less than 4 mm and the cleat height (d_2) shall not be less than 2.5 mm for type 1.

When tested in accordance with **IS 15298 (Part 1)**, the thickness (d_1) shall not be less than 4 mm and the cleat height (d_2) shall not be less than 6 mm for type 2.

In case of PU -rubber double density sole, the effective thickness of rubber shall not be less than 2mm.

(Page 4, clause 5.16.7) — Substitute the existing clause with the following clause:

When outsoles are tested in accordance with **IS 15298 (Part1)**, the relative volume loss shall not be greater than 200 mm³.

(Page 6, Annex-A) — Add the following at the end:

IS No.

Title

IS 390: 2024 Textile Fabrics — Determination Of Resistance To Surface Wetting (Spray Test)

IS 7016(Part 7) Methods Of Test For Rubber Or Plastics Coated Fabrics Part 7 Determination Of
Resistance To Penetration By Water (Third Revision)