

BUREAU OF INDIAN STANDARDS
DRAFT FOR COMMENTS ONLY

(Not to be reproduced without the permission of BIS or used as a standard)

Draft Indian Standard
Winding Wires for Submersible Motors — Specification
Part 4 Specification for Individual Wires
Section 3 Polyester and polypropylene insulated winding wires
(Second Revision of IS 8783 Part 4/Sec 3)

Winding Wire Sectional
Committee, ETD 33

Last date for comments: 30-10-2025

FOREWORD

(Formal clauses of the draft will be added later)

This standard was initially published in 1978, covering PVC insulated winding wires for submersible motors designed for 85 °C operation. Subsequently, two related standards—IS 10051 : 1981, Specification for PVC insulated winding wires for submersible motors for 105 °C operation, and IS 12788 : 1989, Specification for PVC insulated winding wires overcoated with nylon for submersible motors—were introduced but later withdrawn.

This part of the series covers the requirements of high conductivity annealed solid and stranded copper conductor with polyester and polypropylene insulated winding wires for submersible motors.

In view of the prolonged absence of revision in the IS 8783 series, the associated winding wire standards for submersible motors are now being revised and circulated for public comments.

Although the committee did not observe significant technical changes in the construction or application of submersible winding wires, it approved wide circulation of the revised drafts with updated normative references to facilitate broader stakeholder consultation for following standards:

IS 8783	Winding wires for submersible motors — Specification
Part 1 : 1995	Part 1 Conductor data
Part 2 : 1995	Part 2 Materials for dielectric and jacket
Part 3 : 1995	Part 3 Methods of tests
Part 4/Sec 1 : 1995	Part 4 Specification for individual wires, Section 1 HR PVC insulated winding wires
Part 4/Sec 2 : 1995	Part 4 Specification for individual wires, Section 2 Cross linked polyethylene insulated and polyamide jacketed wires
Part 4/Sec 3 : 1995	Part 4 Specification for individual wires, Section 3 Polyester and polypropylene insulated winding wires

This revision includes the incorporation of amendments.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Draft Indian Standard

WINDING WIRES FOR SUBMERSIBLE MOTORS – SPECIFICATION

PART 4 SPECIFICATION FOR INDIVIDUAL WIRES

SECTION 3 POLYESTER AND POLYPROPYLENE INSULATED WINDING WIRES

(Second Revision of IS 8783 Part 4/Sec)

1 SCOPE

This draft standard (Part 4/Sec 3) covers the requirements of high conductivity annealed solid and stranded copper conductor with polyester and polypropylene insulated winding wires for submersible motors.

The wires covered in this standard are suitable for use where the combination of ambient temperature and temperature rise due to load results in conductor temperature not exceeding 105 °C.

2 REFERENCES

The standards listed in Annex A contain provisions, which through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent editions of the standards.

3 GENERAL

3.1 The tests on insulated winding wires shall be carried out in accordance with IS 8783 (Part 3): 1995.

3.2 Conductors for this type of wires shall conform to IS 8783 (Part 1).

3.3 Requirements of dielectric materials shall conform to type 3 of IS 8783 (Part 2).

4 REQUIREMENTS

4.1 Thickness of Insulation

The minimum thickness of insulation shall not be less than the minimum value (t_i) specified in Tables 1 and 2 as relevant.

4.2 Application of Insulation

The insulation shall be so applied that it fits closely on the conductor and it shall be possible to remove it without damage to the conductor.

4.3 Colour

The colour of insulation of winding wire shall be natural.

4.4 Overall Diameter

The overall diameter of winding wire shall not exceed the maximum value specified in Table 1 and 2.

4.5 High voltage Test (Water immersion Test)

The wires shall withstand the test at room temperature when an a.c. voltage of 3Kv at frequency of 50 Hz is applied for one minute after immersion of the wire for minimum 12 h in water.

4.6 The overall surface of finished winding wires shall be reasonably smooth.

5 PACKING

The winding wire shall either be wound on spools/reels conforming to 14841 series or supplied in coils packed and labelled.

Table 1 Insulation Thickness and Overall Diameter of Wires with Round Solid Conductor
(Clauses 4.1 and 4.4)

Sl No.	Cross-sectional Area	Nominal Conductor Diameter	Thickness of Insulation, (t_i)			Overall Diameter, Max
			Thickness of Polyester, Min	Thickness of Polypropylene, Min	Total Thickness of Insulation, Min	
	mm ²	mm	mm	mm	mm	mm
(1)	(2)	(3)	(4)	(5)	(6)	(7)
i)	0.125	0.4	0.05	0.10	0.20	0.90
ii)	0.159	0.45	0.05	0.10	0.20	0.95
iii)	0.196	0.5	0.05	0.10	0.20	1.00
iv)	0.238	0.55	0.05	0.10	0.20	1.05
v)	0.283	0.6	0.05	0.10	0.20	1.10
vi)	0.332	0.65	0.05	0.10	0.20	1.15
vii)	0.385	0.7	0.05	0.10	0.20	1.20
viii)	0.442	0.75	0.05	0.10	0.20	1.25
ix)	0.502	0.8	0.05	0.10	0.20	1.30
x)	0.638	0.9	0.05	0.10	0.20	1.40
xi)	0.769	0.95	0.05	0.10	0.20	1.45
xii)	0.785	1	0.05	0.10	0.20	1.50
xiii)	0.85	1.1	0.05	0.10	0.20	1.60
xiv)	1.13	1.2	0.05	0.10	0.20	1.70
xv)	1.33	1.3	0.05	0.10	0.20	1.80
xvi)	1.54	1.4	0.05	0.15	0.25	2.00
xvii)	1.77	1.5	0.05	0.15	0.25	2.10
xviii)	2.01	1.6	0.05	0.15	0.25	2.20

Sl No.	Cross-sectional Area	Nominal Conductor Diameter	Thickness of Insulation, (t_i)			Overall Diameter, Max
			Thickness of Polyester, Min	Thickness of Polypropylene, Min	Total Thickness of Insulation, Min	
	mm ²	mm	mm	mm	mm	mm
xix)	2.27	1.7	0.05	0.15	0.25	2.30
xx)	2.54	1.8	0.05	0.15	0.25	2.40
xxi)	2.84	1.9	0.05	0.15	0.25	2.50
xxii)	3.14	2	0.05	0.15	0.25	2.60
xxiii)	3.46	2.1	0.05	0.15	0.25	2.70
xxiv)	3.8	2.2	0.05	0.15	0.25	2.80
xxv)	4.15	2.3	0.07	0.17	0.30	3.10
xxvi)	4.52	2.4	0.07	0.17	0.30	3.20
xxvii)	4.91	2.5	0.07	0.17	0.30	3.30
xxviii)	5.31	2.6	0.07	0.17	0.30	3.40
xxix)	5.73	2.7	0.07	0.17	0.30	3.50
xxx)	6.16	2.8	0.07	0.17	0.30	3.60
xxxi)	6.61	2.9	0.07	0.17	0.30	3.70
xxxii)	7.67	3	0.07	0.17	0.30	3.80
xxxiii)	7.55	3.1	0.07	0.17	0.30	3.90
xxxiv)	8.04	3.2	0.07	0.17	0.30	4.00
xxxv)	8.55	3.3	0.07	0.17	0.30	4.10
xxxvi)	9.08	3.4	0.07	0.17	0.30	4.20
xxxvii)	9.62	3.5	0.07	0.17	0.35	4.30
xxviii)	10.18	3.6	0.10	0.20	0.35	4.50
xxxix)	10.75	3.7	0.10	0.20	0.35	4.60
xl)	11.34	3.8	0.10	0.20	0.35	4.70
xli)	11.95	3.9	0.10	0.20	0.35	4.80
xl ii)	12.57	4	0.10	0.20	0.35	4.90
xl iii)	13.2	4.1	0.10	0.20	0.35	5.00
xl iv)	13.85	4.2	0.10	0.20	0.35	5.20
xl v)	15.21	4.4	0.10	0.20	0.35	5.40
xl vi)	16.62	4.6	0.10	0.20	0.35	5.50
xl vii)	18.1	4.8	0.10	0.20	0.35	5.70
xl viii)	19.64	5	0.10	0.20	0.35	6.00

Table 2 Insulation Thickness and Overall Diameter of Wires with Stranded Conductor
(Clauses 4.1 and 4.4)

Sl No.	Conductor Composition No. of Wires x Wire Dia	Cross-Sectional Area, Nominal	Nominal Conductor Diameter	Thickness of Insulation, (t_i)			Overall Diameter
				Polyester	Polypropylene	Total	
	mm	mm ²	mm	mm, Min	mm, Min	mm, Min	mm, Max
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)
i)	19 x 0.49	3.58	2.45	0.07	0.17	0.30	3.1
ii)	19 x 0.52	4.04	2.60	0.07	0.17	0.30	3.3
iii)	19 x 0.55	4.51	2.75	0.07	0.17	0.30	3.4
iv)	19 x 0.58	5.02	2.90	0.07	0.17	0.30	3.6
v)	19 x 0.61	5.55	3.05	0.07	0.17	0.30	3.8
vi)	19 x 0.64	6.11	3.20	0.10	0.20	0.35	4.0
vii)	19 x 0.68	6.90	3.40	0.10	0.20	0.35	4.2
viii)	19 x 0.73	7.95	3.65	0.10	0.20	0.35	4.5
ix)	19 x 0.78	9.08	3.90	0.10	0.20	0.35	4.7
x)	19 x 0.82	10.03	4.10	0.10	0.20	0.35	4.9
xi)	19 x 0.90	12.09	4.50	0.10	0.25	0.40	5.6
xii)	19 x 0.94	13.18	4.70	0.10	0.25	0.40	5.8
xiii)	19 x 0.97	14.00	4.85	0.10	0.25	0.40	5.9
xiv)	19 x 1.00	14.92	5.00	0.10	0.25	0.40	6.1
xv)	19 x 1.04	16.14	5.20	0.10	0.25	0.40	6.3
xvi)	19 x 1.10	18.06	5.50	0.15	0.25	0.45	6.6
xvii)	19 x 1.16	20.08	5.80	0.15	0.25	0.45	6.9
xviii)	27 x 1.00	21.21	6.15	0.15	0.25	0.45	7.3
xix)	27 x 1.10	25.67	6.80	0.15	0.30	0.50	8.2

6 MARKING

6.1 The winding wire shall carry following information marked on the label on spool/reel:

- Reference to this Indian Standard for example IS 8783 (Part 4/Sec 3);
- Manufacturer's name, brand name or trade-mark;
- Size of conductor/maximum overall diameter, area, number of strands as applicable;
- Length of conductor on spool/reel;
- Number of lengths on spool/reel (if more than one);
- Approximate gross mass;
- Country of manufacture; and
- Year of manufacture.

6.2 BIS CERTIFICATION MARKING

The product(s) conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the Bureau of Indian Standards Act, 2016 and the Rules and Regulations framed thereunder, and the products may be marked with the Standard Mark.

ANNEX A
(Foreword)

LIST OF REFERRED STANDARDS

<i>IS No.</i>	<i>Title</i>
14841 series	Packaging of winding wires
8783 (Part 1) : 1995	Winding wires for submersible motors — Specification Part 1 conductor data (<i>first revision</i>)
8783 (Part 2) : 1995	Winding wires for submersible motors — Specification Part 2 Materials for dielectric and jacket (<i>first revision</i>)
8783 (Part 3) : 1995	Winding wires for submersible motors — Specification Part 3 Methods of tests (<i>first revision</i>)
IS 8783 (Part 4/Sec 2 : 1995	Winding wires for submersible motors — Specification Part 4 Specification for individual wires Section 2 crosslinked polyethylene insulated and polyamide jacketed wires (<i>first revision</i>)