भारतीय मानक ब्यूरो BUREAU OF INDIAN STANDARDS

Draft for comments only

Doc. No: TXD 08 (24028)

February 2024

(Not to be reproduced without permission of BIS or used as Standard)

भारतीय मानक मसौदा

वस्त्रादि – हथकरघा सूती इंगरी कपड़ा – विशिष्टि

(आई एस 749 का दूसरा पुनरीक्षण)

Draft Indian Standard

TEXTILES — HANDLOOM COTTON DUNGRI CLOTH — SPECIFICATION

(Second Revision of IS 749)

ICS 59.080.30

Handloom and khadi sectional committee,	Last date for receipt of comment is
TXD 08	14 April 2024

FOREWORD

(Formal clauses will be added later)

Handloom cotton dungri cloth is commonly used to create traditional Indian attire such as kurtas, salwar suits, and dresses.

This standard was originally published in 1955 and subsequently revised in 1978. The standard has again been revised to incorporate the following changes:

a) Test method for identification of material has been incorporated;

- b) Marking clause has been modified;
- c) Sampling clause has been modified; and
- d) References to Indian Standards have been updated.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test, shall be rounded off in accordance with IS 2: 2022 'Rules for rounding off numerical values (*second revision*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1 SCOPE

- **1.1** This standard prescribes the constructional particulars and other requirements of three varieties of handloom cotton dungri cloth, grey, bleached or dyed.
- **1.2** This standard does not specify the general appearance, feel, finish, etc, of the cloth (*see also* **4.3**).

2 REFERENCES

The standards listed in Annex A contain provisions which, through reference in this text, constitute provisions of this standard. At the time of publication, the editions indicated were valid. All standards are subject to revision and parties to agreements based on this standard are encouraged to investigate the possibility of applying the most recent edition of the standards indicated in Annex A.

3 MANUFACTURE

3.1 Yarn

The cotton yarn used in the manufacture of dungri cloth shall be satisfactory in evenness and reasonably free from neps and spinning defects. The yarn shall conform to Grade C of IS 171.

3.2 Cloth

The cloth shall be free from dressing and filling materials and from substances liable to cause subsequent tendering.

4 REQUIREMENTS

4.1 The constructional particulars of dungri cloth shall conform to those given in Table 1.

Table 1 Constructional Particulars of Handloom Cotton Dungri Cloth

(*Clause* 4.1)

Variety No.	Count of yarn [Cotton Count (Universal Count)]		Ends/ cm	Picks/ cm	Length	Width	Weave
	Warp	Weft					
(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)
					m	cm	
1	20s (30 tex)	20s (30 tex)	20	16	as ed	or as	2/2 Twill
2	$20s/2 (30 \text{ tex} \times 2)$	20s (30 tex)	12	9 (double)	20 or agree	5, 90 c agree	Plain
3	$20s/2 (30 \text{ tex} \times 2)$	10s (59 tex)	10	11		4(plain
_	± 5	± 5	± 5	± 5		± 2	
	IS 344	2	IS	1963	IS	1954	Visual
	(2) 1 2	No. (Universal (Warp (2) (3) 1 20s (30 tex) 2 20s/2 (30 tex × 2) 3 20s/2 (30 tex × 2) ± 5	No. (Universal Count)] Warp Weft (2) (3) (4) 1 20s (30 tex) 20s (30 tex) 2 20s/2 (30 tex × 2) 20s (30 tex) 3 20s/2 (30 tex × 2) 10s (59 tex)	No. (Universal Count)] cm Warp Weft (2) (3) (4) (5) 1 20s (30 tex) 20s (30 tex) 20 2 20s/2 (30 tex × 2) 20s (30 tex) 12 3 20s/2 (30 tex × 2) 10s (59 tex) 10 — ± 5 ± 5 ± 5	No. (Universal Count)] cm cm Warp Weft (2) (3) (4) (5) (6) 1 $20s (30 \text{ tex})$ $20s (30 \text{ tex})$ 20 16 2 $20s/2 (30 \text{ tex} \times 2)$ $20s (30 \text{ tex})$ 12 9 (double) 3 $20s/2 (30 \text{ tex} \times 2)$ $10s (59 \text{ tex})$ 10 11 — ± 5 ± 5 ± 5 ± 5	No. (Universal Count)] cm cm Warp Weft (2) (3) (4) (5) (6) (7) 1 $20s (30 \text{ tex})$ <td>No. (Universal Count)] cm cm Cm Warp Weft (2) (3) (4) (5) (6) (7) (8) (1) (2) (3) (4) (5) (6) (7) (8) (1) </td>	No. (Universal Count)] cm cm Cm Warp Weft (2) (3) (4) (5) (6) (7) (8) (1) (2) (3) (4) (5) (6) (7) (8) (1)

- **4.2** The colour fastness ratings and other requirements of cloth shall conform to those given in Table 2.
- **4.3** If order to illustrate or specify the indeterminable characteristics, such as general appearance, lustre, feel and shade of the cloth, a sample has been agreed upon and sealed, the supply shall be in conformity with the sample in such respects.

Table 2 Requirements of Handloom Cotton Dungri Cloth

(*Clause* 4.2)

Sl No.	Characteristic	Requirement	Method of Test, Ref to
(1)	(2)	(3)	(4)
i)	Colour fastness to:		
	a) Light	5 or better	IS/ISO 105-B01 or
			IS/ISO B02
	b) Washing Test 4	4 or better	IS/ISO 105-C10
ii)	Dimensional change,	4.0	IS 2977
	percent, Max		
iii)	Scouring loss, percent, <i>Max</i> :		IS 1383
	a) Grey	10	
	b) Bleached or dyed	2.5	
iv)	pH value of aqueous extract	6.0 or 8.5	IS 1390
v)	Fibre identification	100 percent cotton	IS 667

4.3.1 The custody of the sealed sample shall be a matter of prior agreement between the buyer and the seller.

5 INSPECTION

- **5.1** The cloth when visually inspected shall be reasonably free from the following defects:
 - a) Weft crack or more than two missing picks across the width of the materials;
 - b) prominently noticeable weft bar due to the fineness in raw material, count, twist, lustre etc;
 - c) More than two adjacent ends running parallel, broken or missing and extending beyond 15 cm;
 - d) prominent selvedge defects;
 - e) Noticeable warp or weft float in the body;
 - f) Noticeable oil or other stains;
 - g) Noticeable cut or tear up to 3 mm in size; and
 - h) Smash rupturing the texture of the fabric.
- **5.1.1** A reference may be made to IS 14466 for details of these defects.

6 SAMPLING

- **6.1** The quantity of handloom cotton dungri cloth of the same variety delivered to a buyer against a despatch not shall constitute a lot.
- **6.2** To ascertain the conformity of the lot to the requirements of this standard, samples shall be drawn and inspected from each lot separately.
- **6.3** The number of pieces to be selected at random for inspection shall be in accordance with Table 3.

Table 3 Sample Size and Permissible Number of Non-Conforming Pieces (*Clause* 6.3)

SI No.	Lot Size	Sample Size	Permissible No. of Non-Conforming Blankets	Sub Sample Size
(1)	(2)	(3)	(4)	(5)
i)	Up to 90	5	0	3
ii)	91 to 150	8	0	3
iii)	151 to 500	13	1	5
iv)	501 to 1200	20	1	5
v)	1201 to 10000	32	2	8
vi)	10001 to 35000	50	3	8
vii)	35001 to 500000	80	5	13
viii)	500001 and	125	7	13
	above			

6.4 Number of Tests and Criterion for Conformity

Sl No.	Characteristic(s)	No. of Tests	Criterion for
			Conformity
(1)	(2)	(3)	(4)
i)	Visual examination, ends, picks, weave, length and width	According to co1 (2) of Table 3	Permissible number of non-conforming piece does not exceed the corresponding number given in co1 (3) of Table 3
ii)	Count of yarn, dimensional change, scouring loss and pH value, colour fastness and fibre identification	According to co1 (4) of Table 3	All the test specimens meet the relevant requirements

7 MARKING

7.1 The cloth shall be suitably marked or labelled with the following information:

- a) Name of the material;
- b) Manufacturer's name, initials or trade-mark;
- c) Length and width of the piece;
- d) Count of warp and weft yarn;
- e) Indication of the source of manufacture; and
- f) Other declarations required as per law in force.

7.2 BIS Certification Marking

The product conforming to the requirements of this standard may be certified as per the conformity assessment schemes under the provisions of the *Bureau of Indian Standards Act*, 2016 and the Rules and Regulations framed thereunder, and the product may be marked with the Standard Mark.

8 PACKING

Unless otherwise agreed upon by the buyer and the seller, the cloth shall preferably be packed in bales or cases in conformity with the procedure laid down in IS 1347 or IS 293.

ANNEX A

(Clause 2)

LIST OF REFERRED INDIAN STANDARDS

IS No.	Title
IS 171: 1993	Textiles — Ring spun grey cotton yarn for weaving — Specification (<i>fourth revision</i>)
IS 293: 1980	Code for seaworthy packaging of cotton yarn and cloth (third revision)
IS 667: 1981	Methods for identification of textile fibres (first revision)
IS 1070: 2023	Reagent Grade Water Specification (fourth revision)
IS 1347: 1972	Specification for inland packaging of cotton cloth and yarn (first revision)
IS 1383 : 2023	Methods for determination of scouring loss in grey and finished cotton textile materials (<i>second revision</i>)
IS 1390 : 2022/ ISO 3071 : 2020	Textiles — Determination of pH of aqueous extract (third revision)
IS 1954 : 1990	Determination of length and width of woven fabrics – Methods (second revision)
IS 1963 : 1981	Methods for determination of threads per unit length in woven fabrics (second revision)
IS 2977: 1989	Fabrics (other than wool) – Method for determination of dimensional changes on soaking in water (<i>first revision</i>)
IS 3442 : 2023	Textiles method for determination of crimp and linear density of yarn removed from fabric
IS 14466 : 1997/ ISO 8498 : 1990	Fabrics — Description of defects — Vocabulary
IS/ISO 105-B01:	Textiles — Tests for colour fastness — Part B01 Colour fastness to light:
2014	Daylight
IS/ISO 105-B02:	Textiles — Tests for colour fastness — Part B02 Colour fastness to
2014	artificial light: Xenon arc fading lamp test
IS/ISO 105-C10 : 2006	Textiles — Tests for colour fastness — Part C10 Colour fastness to washing with soap or soap and soda