

TERMS OF REFERENCE FOR R&D PROJECT

Petroleum, coal and related products department, Methods of sampling and test for plastics sectional Committee, PCD 27

1) Title of the Project

Study on Specific migration from different types of plastic packaging materials intended for food contact applications.

2) Introductory Background

Plastic packaging materials are extensively used in food packaging due to their mechanical strength, barrier properties, and adaptability. However, the migration of substances surpassing the safe limit from these plastics into food may pose a potential health risk, which is regulated under FSS Packaging regulations, 2018 when tested as per IS 9845:1998. The Standard prescribes methods for evaluating overall migration under specified conditions using specified food simulants.

Considering the diverse climatic conditions in India and the nature of the distribution chain, plastic packaging is often subjected to extreme environmental conditions such as high temperature and humidity. These factors can significantly influence migration behaviour. While standard test conditions are defined in IS 9845, it is imperative to evaluate the performance of packaging materials under more extreme Indian conditions to validate the adequacy of current limits. Specific migration refers to the release of particular substances from packaging materials into food under certain conditions.

Given the variety of packaging materials used in the Indian market and the possibility of exposure to extreme environmental conditions during storage and distribution, there is a need to evaluate migration behaviour under both standard test conditions and elevated conditions simulating Indian climatic extremes.

This project aims to undertake comprehensive specific migration testing across a variety of packaging types and under both standard and extreme conditions, as specified in **Annex A**.

3) Objective

To assess the specific migration of substances from various plastic packaging materials intended for food contact applications as per Annex A under:

- Standard test conditions as prescribed in IS 9845, and
- Extreme conditions.

4) Scope

- a) Identification of packaging material manufacturers, converters, and brand owners across the Indian market for packaging specified in Annex A.
- b) Collection of representative samples of plastic packaging used for food contact, based on classifications provided in Annex A.
- c) Identification of laboratory/laboratories accredited to IS/ISO/IEC 17025 capable of conducting specific migration testing under extreme conditions (temperatures higher than those specified in IS 9845) as per Annex A.
- d) Conducting specific migration testing on each packaging material under conditions specified in Annex A.
- e) Comparison of migration results obtained under both Standard test conditions and extreme conditions.
- f) Preparation of a final report outlining observations from testing.

5) Testing Methodology

- a) Source plastic packaging material samples (details as per Annex A) through engagement with manufacturers, brand owners.
- b) Coordinate with laboratory/laboratories accredited to IS/ISO/IEC 17025 to conduct testing as specified in Annex A.
- c) Ensure uniformity in sampling and replication across both standard conditions and extreme climatic test conditions.
- d) Analyse test data to understand variation in migration behaviour.

6) Expected Deliverables

- a) Comprehensive R&D report covering:
 - Packaging types tested (as per Annex A)
 - Test methods, conditions (standard and extreme), and simulants used (as per Annex A)
 - Test results and analysis; and
 - Comparative evaluation of standard vs. extreme condition outcomes

b) Annexures containing:

- Source-wise details of packaging samples
- Raw test data and laboratory reports; and
- Photographs and documentation of testing.

7) Timeline and Method of Progress Review

Total Duration: 4 months

Stage I – End of 1st Month

- Submission of inception report including manufacturer details, sample plan, identified labs.

Stage II – End of 3rd Month

- Progress report detailing sample collection and preliminary testing results.

Final Stage – End of 4th Month

- Final comprehensive report with all test results and analysis.

8) Support from BIS:

- a) BIS will provide access to relevant Indian and international standards.
- b) BIS will facilitate communication with manufacturers, testing laboratories, and user industries for support.

9) Nodal Officer:

Shri Shivam Dwivedi, Sc. C/Deputy Director, PCD, BIS, may be contacted at [pcd@bis.gov.in/pcd27@bis.gov.in] for any queries related to the research project.

ANNEX A

Specific Migration Testing - Under Extreme Climatic Condition - In line with FSSAI Metals & DEHP test as per IS 9845 & EN 13130-1										
Category	Sample No	Sample Category	Product	Temperature C	Simulant	Simulant category (IS 9845)	Time	No of samples to be tested	Cumulative	Elements & its limits
1	1	PET Bottle	Water	40	Distilled water or water of equivalent quantity	A	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max.

	2			70	Distilled water or water of equivalent quantity	A	10 days	3	6	0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA - 10 ppb - EN 13130-13
2	3	PET Bottle	Carbonated Soft Drink	40	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0

	4			70	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3	12	mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA - 10 ppb - EN 13130-13
3	5	PET Bottle	Alcohol 10%	40	10% Ethanol in Aqueous solution (v/v)	C1	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg

	6			70	10% Ethanol in Aqueous solution (v/v)	C1	10 days	3	18	3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) <u>BPA - 10 ppb -EN 13130-13</u>
4	7	R-PET Bottle (30%)	Water	40	Distilled water or water of equivalent quantity	A	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg

	8			70	Distilled water or water of equivalent quantity	A	10 days	3	24	4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb -EN 13130-13
5	9	R-PET Bottle (30%)	Carbonated Soft Drink	40	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0

	10			70	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3	30	mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb - EN 13130-13
6	11	R-PET Bottle (30%)	Alcohol 10%	40	10% Ethanol in Aqueous solution (v/v)	C1	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0

	12			70	100% Ethanol in Aqueous solution (v/v)	C1	10 days	3	36	mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb - EN 13130-13
7	13	Polycarbonate Cans 20L	Water	40	Distilled water or water of equivalent quantity	A	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6

	14			70	Distilled water or water of equivalent quantity	A	10 days	3	42	mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb EN 13130-13
8	15	Laminate with Food Contact Coating	Aqueous	40	Distilled water or water of equivalent quantity	A	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg

	16			70	Distilled water or water of equivalent quantity	A	10 days	3	48	5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb -EN 13130-13
8	17	Laminate with Food Contact Coating	Acidic	40	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0

	18			70	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3	54	mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb - EN 13130-13
8	19	Laminate with Food Contact Coating	Fatty	38	n heptane -freshly distilled before use	D	30 min	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6
	20			45	n heptane -freshly distilled before use	D	30 min	3		

	21			55	n heptane -freshly distilled before use	D	30 min	3	63	mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb- EN 13130-13
9	22	Laminate with sealant film	Snacks	38	n heptane -freshly distilled before use	D	30 min	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg

	23			45	n heptane -freshly distilled before use	D	30 min	3		3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0
	24			55	n heptane - freshly distilled before use	D	30 min	3	72	mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb - EN 13130-13
9	25	Laminate with sealant film	Water / Sugar syrup	40	Distilled water or water of equivalen t quantity	A	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg

	26			70	Distilled water or water of equivalent quantity	A	10 days	3	78	2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg)
										BPA 10 ppb -EN 13130-13

9	27	Laminate with sealant film	Pickles	40	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg)
	28			70	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3	84	

										BPA - 10 ppb EN 13130-13
10	29	Film / Laminate	Filled Pickle Pack Market sample - Kirana Shop	NA	NA	NA	NA	3	Will be checked in CIPET by Ultra Highperformance Liquid Chromatography or equivalent instrument for migration	<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2

										ethylhexyl) ester (DEHP-Max 1.5 mg/kg)
--	--	--	--	--	--	--	--	--	--	--

										BPA 10 ppb - EN 13130-13
--	--	--	--	--	--	--	--	--	--	-----------------------------

11	30	PE Fillm LD / LLD	Aqueous	40	Distilled water or water of equivalent quantity	A	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb - EN 13130
	31			70	Distilled water or water of equivalent quantity	A	10 days	3	90	

11	32	PE Fillm LD / LLD	Acidic	40	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb - EN 13130
	33			70	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3	96	

11	34	PE Film LD / LLD	Fatty	38	n heptane -freshly distiiled before use	D	30 min	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0
----	----	------------------	-------	----	---	---	--------	---	--	---

	35			45	n heptane -freshly distiiled before use	D	30 min	3		mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb EN 13130-13
	36			55	n heptane -freshly distiiled before use	D	30 min	3	105	

12	37	PE EVOH	Aqueous	40	Distilled water or water of equivalent quantity	A	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0
----	----	---------	---------	----	---	---	---------	---	--	--

	38			70	Distilled water or water of equivalent quantity	A	10 days	3	111	mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb EN 13130-13
--	----	--	--	----	---	---	---------	---	-----	--

12	39	PE EVOH	Acidic	40	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0
----	----	---------	--------	----	---	---	---------	---	--	--

	40			70	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3	117	mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb -EN 13130-13
--	----	--	--	----	---	---	---------	---	-----	---

12	41	PE EVOH	Fatty	38	n heptane -freshly distilled before use	D	30 min	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6
	42			45	n heptane -freshly distilled before use	D	30 min	3		
	43			55	n heptane - freshly distilled before use	D	30 min	3	126	mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb -EN 13130-13

13	44	CPP	Aqueous	40	Distilled water or water of equivalent quantity	A	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg
	45			70	Distilled water or water of equivalent quantity	A	10 days	3	132	
										9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb - EN 13130-13

13	46	CPP	Acidic	40	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg)
	47			70	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3	138	

										BPA 10 ppb EN 13130-13
13	48	CPP	Fatty	38	n heptane -freshly distilled before use	D	30 min	3		<u>As per FSSAI requirements:</u> 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg
	49			45	n heptane -freshly distilled before use	D	30 min	3		

	50			55	n heptane -freshly distilled before use	D	30 min	3	147	6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg)
										BPA 10 ppb - EN 13130-13

14	51	Laminate with sealant film	Pickles - Hot fill	100	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	2 hr	3	As per FSSAI requirements: 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb - EN 13130-13
----	----	----------------------------------	-----------------------	-----	---	---	------	---	--

15	52	Laminate with sealant film	Pickles - Hot fill	70	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10 days	3	153	As per FSSAI requirements: 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA 10 ppb -EN 13130-13
----	----	----------------------------------	-----------------------	----	---	---	------------	---	-----	---

	53	Laminate with Sealant film	Fruit juices - Hot fill	100	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	2 hr	3		As per FSSAI requirements: 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA : 10 ppb EN 13130-13
--	----	----------------------------------	----------------------------	-----	---	---	------	---	--	---

	54	Laminate with Sealant film	Fruit juices - Hot fill	70	3% Acetic Acid (w/v) in aqueous solution (using simulant A)	B	10days	3	159 (53)	As per FSSAI requirements: 1. Barium - Max. 1.0 mg/kg 2. Cobalt - Max. 0.05 mg/kg 3. Copper - Max. 5.0 mg/kg 4. Iron - Max. 48.0 mg/kg 5. Lithium - Max. 0.6 mg/kg 6. Manganese - Max. 0.6 mg/kg 7. Zinc - Max. 25.0 mg/kg 8. Antimony-Max 0.04 mg/kg 9. Phthalic Acid, bis(2 ethylhexyl) ester (DEHP-Max 1.5 mg/kg) BPA : 10 ppb EN 13130-13
Guidelines: Test Method :1. Simulant Selection IS 9845 2. Worst Case Condition EN 13130-1 & EU 10 /2011 Contact time and Temperature 3. Specific Migration identification and Quantification IS 3025-2 (metals), ISO 18856 (DEHP) and EN 13130-13 (BPA)										